RG104 E-1 Box 121

1880

Weekly Report of Silver Purchases and Deposits Melted at United States Mint.

Date.	Assay No.	Name of Depositor.	Weight before Melting. Oz.	Dec.	Weight after Melting. Oz.	Dec.	Loss. Oz.	Dec.	Loss per ct.	Gain. Oz.	Dec.	Description of Bullion.	Notes of Melter and Refiner. 22/4/80
Aprie	5th 151	Isaac G. Gerhart, Prest.	102	90	102	60		30	29			Bor. Coin	The deposits are
		2 G. 6. Thompson Remelt 625.45	656	55	635	10	31	45	4 79			Bar Gyld	as follows:
	6th	3 Jas. De Turck	228	95	228	35		60	26			Bor. Coin	6 of finer bullion
		4 G. 6. Thompson	100	10	99	70		40	40			Shorts, Pl. &c.	with a moderate
		5 Geo. Cohen	53	95	52	85	1	10	2 04			Do	average of 0.23%;
		6 Simons, Bro. & Co.	42	60	42	50		10	23			Do	6 of coin with the
		7 Sailer & Stevenson	1014	60	1014	60						Bars, U.S.A. C. N.Y.	usual average
	8th	8 G. 6. Thompson	56	45	56	25		20	36			Rings	loss of 0.22%;
		9 E. S. Jahn	113	20	111	55	1	65	1 46			Pick Cases, Bor. Coin,	do.
	9th	60 G. 6. Thompson	435	80	435	15		65	15			Bor. Coin	5 of plate with a
	10th	1 Sailer & Stevenson	1049	05	1049	05						Bars, U.S.A. C. N.Y.	low average loss
			4857	15	4817	70	36	45	131				of 0.69%;
													9 of base bullion
													with a full average
													wastage of 44%.
													2 of the N.Y. Assay
													Office, — losses not
													noted.
													28 Deposits in all.
													J. C. Booth
													M.R.

Transferred to Bullion fund during the evening 82,409.95 Oz, Newark Bars and Foreign Coin which weighed 3,442.90 Oz, before melting and 3,459.90 Oz, after.

For week ending Aprie 10th 1880.

Date.	Assay No.	Name of Depositor.	Weight before Melting. Oz.	Dec.	Weight after Melting. Oz.	Dec.	Loss. Oz.	Dec.	Loss per ct.	Gain. Oz.	Dec.	Description of Bullion.	Notes of Melter and Refiner.
Aprie	12th 162	Wm. H. Lee	53	40	53	30		10	19			Ring	
		3 G. 6. Thompson	25	65	25	10		55	2 12			Pick Cases, Pl. &c.	
		4 Do	94	05	92	75	1	30	1 38				
		5 Do	957	50	878	35	76	15	7 98			Bars Gyld	
		6 Do	328	85	328	40		45	14			Bor. Coin	
		7 Carrow, Bishop & Co.	140	10	140	00		10	07			Bars	
	13th	8 G. 6. Thompson	51	25	50	90		35	69			Shorts, Pl. &c.	
		9 Thos R. Lee	308	90	308	45		45	15			Bars	
	14th	70 G. 6. Thompson	46	35	46	30		05	11			Pl. &c. Gyld	
		1 Do	105	70	99	50	6	20	5 85			Pick Cases, &c.	
		2 John Stuerly	99	30	98	95		25	25			Ring	
	15th	3 G. 6. Thompson	504	20	487	60	16	60	3 29			Bars Pick Cases.	
	16th	4 Do	181	55	174	75	6	80	3 74			Grs. L. Superintr.	
		5 Hastings & Co.	142	40	131	70	10	70	7 54			Skewings	
		6 Wm. H. Lee	83	60	83	30		30	36			Bars & Buttons	
		7 Joel S. Bailey & Co.	153	20	152	70		50	33			Bor. Coin	
	17th	8 G. 6. Thompson	60	00	59	90		10	17			Bor. Coin	
			3332	90	3211	95	120	95	3 63				

Transferred to Bullion fund during the week 53,790.40 Oz, Omaha; 43,370.10 Oz, Pennsylvania Lead Company; 7,293.61 Oz, Platt; 54,786.95 Oz, St. Louis; 15,307.60 Oz, Boston & Colorado; 89,681.75 Oz, Newark; Foreign Coin which weighed before melting 2261 Oz, and 2257.70 Oz, after, and Arizona Bars which weighed before melting and drying 4545 Oz, and 4533.65 after.

For week ending Aprie 17th 1880.

J. Robley Dunglison Register

RG104 E-1 Box 121

Report of Silver Purchases
Deposits melted for weeks
ending:

April 10th 1880

April 17th 1880

NARA RG104, Entry 1, Box 121

[Abstract:] Report of Silver Purchases & Deposits melted for weeks ending: -

April 10, 1880
April 17, 1880

Weekly Report of Silver Purchases and Deposits Melted at United States Mint.

[Please see original images for data table.]